



**POLYLABS™**

## BIO POLYOL EGT 345

Advancing Sustainable PU Production

### Technical Data Sheet

**Bio Polyol EGT 345** is a polyester linear polyol derived from second-generation feedstocks—forestry by-products that do not compete with food supply chains. Tailored as an additive for rigid PU foam systems and other applications, it radically reduces CO<sub>2</sub> footprints in PU products.

#### Key advantages:

- Low Carbon Footprint -1.2 KgCO<sub>2</sub>eq/kg.
- Bio carbon content 96 %.
- Increased solubility with pentanes as well as with HFO blowing agents.
- Reduce viscosity in PU systems.
- Primary and secondary OH groups.
- Green production in an eco-friendly process.

Technical properties	Value	Measurement unit	Based on method
CO <sub>2</sub> footprint	-1.2	KgCO <sub>2</sub> eq/kg	Internal CO <sub>2</sub> calculation
Bio carbon content	96	%	Estimation
Hydroxyl number	335 – 355	mgKOH/g	DIN 53240
Acid number	< 5	mgKOH/g	DIN 53402
Density at 20°C	972	kg/m <sup>3</sup>	DIN 51757
Viscosity at 25 °C	150 – 210	mPa·s	DIN 53015
Functionality	2.0		Estimation
Water content	< 0.2	wt. %	DIN 51777
Avg. molecular weight	240 - 440	Da	GPC
Shelf life	Shelf Life of 6 months for packaged material stored at ambient temperatures of < 30°C.		
Storage	Bio Polyol EGT 345 is hygroscopic. Container should be sealed at all times unless discharging.		

The CO<sub>2</sub> footprint provided is based on a Cradle-to-Gate assessment, including raw material sourcing, transportation, and production emissions.

Carbon footprint includes biogenic CO<sub>2</sub>. Calculations excluding biogenic CO<sub>2</sub> are available upon request, in accordance with customer requirements.

**PolyLabs SIA, 46 Mukusalas street, Riga, LV-1004, Republic of Latvia, EU** [www.polylabs.eu](http://www.polylabs.eu)

All information and data, including the formulations and procedures discussed herein, are believed to be correct. However, this should not be accepted as a guarantee of their accuracy, and confirming tests should be run in your laboratory or plant. No statement should be construed as a recommendation for any use which would violate any patent rights. Sales of all products are pursuant to terms and conditions included in PolyLabs SIA. sales documents. Nothing contained therein shall constitute a guarantee or warranty with respect to the products described or their use. Safety information regarding these products is contained in their Material Safety Data Sheets. Users of these products are urged to review and use this information.